

PRODUCT DATA

FASSON®

FASSON® Offset & Laser MC White FSC® Certified

Issued May 2021

Introduction

A premium-quality, machine-coated woodfree paper, semi-gloss, white.

Description

Face: A premium-quality, machine-coated woodfree, white paper with a semi-gloss finish. This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

Availability

Adhesive ➡ Permanent

Backing U

No cracklines

x

Printing & Conversion

Offset printing.

Laser printing/

Dry toner copiers:

Suitable for most popular models. Tightly defined release characteristics avoid pre-dispensing during the printing process.

Inkjet printing:

Some models of desktop inkjet printers have paper thickness limitations, which can cause feed problems.

Before applying the label, the surface must be clean, dry and grease-free.

Note:

Please test the self-adhesive construction first to confirm compatibility.

Features:

Excellent lay flatness, enabling high-speed printing

Excellent guillotining and kiss-die cutting performance.

Fast drying paper, enabling quick finishing (like cutting, die-cutting etc.)

High temperature resistant adhesive (up to 180°C) enabling proper paper transport through dry toner copiers/-laser printers.

Recommendations for use

A variety of labels for: barcoding, addressing, inventory, product identification labels and other variably imprinted messages.

For indoor use.

General

Shelf life: 2 years stored at 20°C / 55% R.H.

Total caliper (±10 %): 164 micron

For information regarding EHS regulation, please visit our website under downloads “Technical bulletins” TB 7.8 Product Compliance Fasson Offset” and for technical guidance “Technical bulletins” – Offset printing.

PRODUCT CHARACTERISTICS

Physical properties

Face

Basis weight:	80 g/m ²	ISO 536
Caliper:	68 micron	ISO 534
Tensile:	5.2 kN/m MD	ISO 1924/2
Opacity:	87 %	ISO 2471

Adhesive

Permanent: General-purpose emulsion-based permanent adhesive with a high initial tack and high adhesion on most common substrates.

Permanent

Adhesion (N/m) (FTM 2 on steel/20 min. bond time)	365
Tack (N/m) (FTM 9 on glass)	380
Minimum application temperature	> +5
Service temperature range up to 24 hrs (°C)	+80
up to 1 hr (°C)	+110
Resistance to cold (°C) ¹⁾ down to	-40

¹⁾ Not fully resistant until after adhesion reaches full strength – after at least 24 hrs.

Backing

No cracklines: A bleached one-side-coated white kraft, especially designed for sheet products, featuring minimal moisture sensitivity.

Basis weight:	78 g/m ²	ISO 536
Caliper:	82 micron	ISO 534

This product, FSC® C011032 certified, is sold as FSC® Mix Credit.

Guarantee and liability:

All product statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. Products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

All products are sold subject to Torraspapel – Lecta's general terms and conditions of sale, see <https://www.lecta.com/terms>

Fasson® and Crack-Back® are registered trademarks of Avery Dennison Corporation and related entities, and the products are produced by Torraspapel - Lecta under license from Avery Dennison Corporation and related entities for EMENA only.